

Technical Data Sheet

MENOS Natural Undercoat No. 626

Range of application	As a primer for interior wooden surfaces. Also suitable for glass fibre wallpaper.
Technical qualities	Elastic, matt. Free of organic chemical compounds according to DIN EN 71, part 9.
Full declaration	Chalk, titan dioxide, isoaliphates, linseed-stand-oil natural resin ester, mica, talcum, silicic acid, dehydrated amino sugar, lemon oil and drying agents free of lead (Ca, Mn, Zr).
Color	White.
Dilution	For spraying SVALOS-Spray Thinner No. 293 or with SVALOS-Thinner No. 222.
Application method	Apply sparingly using a brush, roller (undiluted) or spraying device (maximum 10 % dilution) at temperatures above 15°C (59°F) and low humidity. Observe further notes on the reverse side!
Coverage	Determine with a test application! One undiluted liter is sufficient for 10-15 m ² (107-154 ft ²), i.e. 80 ml/m ² . The consumption could be considerably more economical depending on the absorbency and the surface condition of the wood. Each dried layer thickness may not exceed 50µm.
Specific gravity	Approximately 1.45 g/ml.
Drying time	At 23 °C (73°F) and 50 % relative humidity, dry to the touch after approximately 3 hours. Sanding and subsequent coating may be done after 24. The paint is fully hardened after 6 - 7 days. A coat applied too thickly, low temperatures or high humidity can cause drying delays.
Cleaning up	Clean equipment immediately after use With SVALOS Thinner No. 222 or LEVO Brush Cleaner No. 997.
Safety advice	<p>Ensure good ventilation during and after application. Always be sure to store cleaning cloths, polishing pads, sponges, etc. that are still wet or even slightly moist with MENOS Natural Undercoat No. 626 in an airtight metal container or in water until their disposal, as there is a danger of spontaneous combustion caused by the plant oil content. The liquid or applied product is not self-ignitable.</p> <p>P102 Keep out of reach of children. P301+P310 IF SWALLOWED: Rinse mouth. Do NOT induce vomiting. Immediately call a doctor. EUH208 Contains lemon oil (d-limonene). Can cause allergic reactions. Emergency number: +49 (0)6132-84463 (24h - GBK GmbH)</p>
Disposal	According to locally regulated laws.
Container sizes	0.05l; 0.375l; 0.75l; 2.5l; 5l.
Storage	Cool and dry. Shelf life: unopened at least 4 years. Oils in opened containers react with oxygen. The less oil is still there, even more so. Residues should be transferred into smaller containers.

How to use

MENOS Natural Undercoat No. 626

Preparation	Surface must be dry (wood moisture content below 15%), solid, clean, and free of grease, resin and dust. If wooden surfaces show small damages or cracks, fill them with ANAVO-Natural Primer No. 628 (or spackle the entire area, if necessary).
Application	Stir thoroughly before use. Apply a sparing base coat of MENOS Natural Undercoat No. 626 with a brush, roller or spraying device at temperatures above 15°C (59°F). Subsequent treatment with VINDO Natural Gloss Paint No. 629 (high gloss).
Renovation	Non-intact old coatings must be completely removed. Follow preparation and application instructions for untreated wood as described above. Sand intact old coatings well and test compatibility by painting with 5 -10 % diluted Natural Gloss Paint No. 629.
Important tips	<p>MENOS Natural Undercoat No. 626 should be applied sparingly. Too thickly applied coatings can impair drying properties and can cause cracking of subsequent paint coats.</p> <p>MENOS Natural Undercoat No. 626 contains little solvent; this may cause a skin formation. Please, remove before stirring. Transfer unused portions into smaller containers for storage. No liability is assumed for possible impaired adhesion as well as the development of odors resulting when MENOS No. 626 is painted over products of other manufacturers or otherwise incompatible undercoats. Do not paint over silicone.</p> <p>MENOS Natural Undercoat No. 626 mixed with 5% by volume of quartz sand will prevent on plaster the penetration of impurities (e.g. nicotine or dried water spots) from the subsurface. Following 1 – 2 applications with DUBRON Natural Dispersion Paint No. 412 or 413.</p>

These directions are the result of long years of research and practical testing. They are backed by our most current expert information. New findings may invalidate this information. The latest version is available on our website at www.livos.de. This data sheet is meant to serve as information and instruction. No legal liability should be interpreted from it. In case of doubt, please contact the LIVOS customer service (see page 1).

February 2023